

General Description and Use		
Argotec SKU Number	49510	
Typical application	Paint, metal & surface protection films	
Polymer	Thermoplastic polyurethane, aliphatic polycaprolactone	
Extrusion method	Flat die	
Gauge	6.0 - 12 mils (150 - 300 microns)	
Width	Up to 62 inches (1.57 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> ■ Smooth and matte surfaces ■ Hard polycaprolactone ■ UV resistant ■ No additives 	
Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 93A
Tensile strength	ASTM D-412	5,000 psi 34.47 MPa
Elongation at break		550%
UV resistance (yellowing)	ASTM D-4329 cycle B ¹	Change in Yellowness Index (ΔYi) <1.5 at 2000 hrs
Gloss, 60°	OTM 3-309	>80

¹ QUV using UVA 340 bulb, 8 hours 70°C, 4 hours 50°C condensation.

Product information revised: January 30, 2018

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.
tel: 413/772-2564 • fax: 413-772-2565 • web: www.swmintl.com • email: ams@swmintl.com

TECHNICAL DATA