

General Description and Use		
Argotec SKU Number	49510-60DV	
Typical application	Outdoor, exposed applications requiring UV resistance	
Polymer	Polycaprolactone-based, aliphatic polyurethane (TPU)	
Extrusion method	Flat-die extrusion	
Gauge	5 - 12 mils (125 - 300 microns)	
Width	Up to 62 inches (1.6 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> ■ Smooth, matte or gloss surfaces ■ Combines soft and hard polycaprolactones ■ UV resistant ■ No additives or processing aids 	
Physical Properties	Test Method	Value
Base Layer		
Hardness	ASTM D-2240	Shore 93A
Tensile strength	ASTM D-412	5000 psi 34.47 MPa
Elongation @ break		550%
UV resistance (yellowing)	ASTM D-4329 cycle B ¹	Change in Yellowness Index (ΔY_i) <1.5 at 2000 hrs
Surface Layer		
Hardness	ASTM D-2240	Shore 60D
Tensile strength	ASTM D-412	7000 psi 48.26 MPa
Elongation @ break		450%
UV resistance (yellowing)	ASTM D-4329 cycle B ¹	Change in Yellowness Index (ΔY_i) <1.5 at 2000 hrs

¹ QUV using UVA 340 bulb, 8 hours 70°C, 4 hours 50°C condensation.

Product information revised: January 30, 2018

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.
tel: 413/772-2564 • fax: 413-772-2565 • web: www.swmintl.com • email: ams@swmintl.com

TECHNICAL DATA