

General Description and Use		
Argotec SKU Number	<b>27303</b>	
Typical application	Textile lamination, die cut and seal	
Polymer	Thermoplastic polyurethane, aromatic polyester	
Extrusion method	Blown film	
Gauge	1.0 - 10 mils (25 - 250 microns)	
Width	Up to 86 inches (2.18 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> <li>■ Smooth surface</li> <li>■ Softest ester</li> <li>■ Low softening temperature</li> </ul>	
Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 78A
Tensile stress @ 100% elongation	ASTM D-412	600 psi 4.14 MPa
Tensile stress @ 300% elongation		1100 psi 7.58 MPa
Tensile strength		5300 psi 36.54 MPa
Elongation at break		700%
Tensile set at 200% E		60%
Tear strength	D-624 <sup>1</sup>	450 pli 78.75 kN/m

<sup>1</sup> Die C.

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.  
tel: 413/772-2564 • fax: 413-772-2565 • web: [www.swmintl.com](http://www.swmintl.com) • email: [ams@swmintl.com](mailto:ams@swmintl.com)