

General Description and Use		
Argotec SKU Number	27370	
Typical application	Elastics	
Polymer	Thermoplastic polyurethane, aromatic polyester	
Extrusion method	Cast film	
Gauge	1.0 - 5 mils (25 - 125 microns)	
Width	Up to 60 inches (1.52 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> ■ Smooth and matte surfaces ■ Soft ester ■ Mid-range softening temperature ■ Low tensile set 	
Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 78A
Tensile stress @ 100% elongation	ASTM D-412	500 psi 3.45 MPa
Tensile stress @ 300% elongation		1500 psi 10.34 MPa
Tensile strength		8000 psi 55.16 MPa
Elongation at break		500%
Tensile set at 200% E		5%
Tear strength	D-624 ¹	430 pli 75.25 kN/m

¹ Die C.

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.
tel: 413/772-2564 • fax: 413-772-2565 • web: www.swmintl.com • email: ams@swmintl.com