

| General Description and Use | | |
|----------------------------------|---|----------------------------|
| Argotec SKU Number | 29102 | |
| Typical application | Die cut and seal | |
| Polymer | Thermoplastic polyurethane, aromatic polyester | |
| Extrusion method | Flat die | |
| Gauge | 5 - 80 mils (125 - 2000 microns) | |
| Width | Up to 60 inches (1.52 meters) | |
| Length | Up to 1000 non-spliced yards (914.4 meters) | |
| Key attributes | <ul style="list-style-type: none"> ■ Matte 2 surface ■ Hard ester ■ High softening temperature | |
| Typical Properties | Test Method | Value |
| Durometer | ASTM D-2240 | Shore 95A |
| Tensile stress @ 100% elongation | ASTM D-412 | 1600 psi 11.03 MPa |
| Tensile stress @ 300% elongation | | 3500 psi 24.13 MPa |
| Tensile strength | | 8000 psi 55.16 MPa |
| Elongation at break | | 450% |
| Tensile set at 200% E | | 17% |
| Tear strength | D-624 ¹ | 600 pli 105.0 kN/m |
| Abrasion resistance | D-1044 ² | 2.6 mg loss |
| Typical melt temperature | | 185 - 192°C 365 - 378°F |

¹ Die C.

² Taber abrasion CS-17 wheel, 1000 gm weight, 1000 cycles.

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.
tel: 413/772-2564 • fax: 413-772-2565 • web: www.swmintl.com • email: ams@swmintl.com