

General Description and Use		
Argotec SKU Number	<b>29285</b>	
Typical application	General purpose with antistatic	
Polymer	Polyurethane	
Hard - soft phase	Aromatic - polyester	
Extrusion method	Blown film	
Gauge	1.0 - 10 mils (25 - 250 microns)	
Width	Up to 86 inches (2.2 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> <li>■ Smooth surface</li> <li>■ Hard ester</li> <li>■ High softening temperature</li> <li>■ Contains antistatic additive</li> </ul>	
Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 90A
Tensile stress @ 100% elongation	ASTM D-412	1600 psi 11.03 MPa
Tensile stress @ 300% elongation		3500 psi 24.13 MPa
Tensile strength		8000 psi 55.16 MPa
Elongation at break		450%
Tear strength	D-624 <sup>1</sup>	600 pli 105 kN/m
Abrasion resistance	D-1044 <sup>2</sup>	2.6 mg loss

<sup>1</sup> Die C.

<sup>2</sup> Taber abrasion CS-17 wheel, 1000 gm weight, 1000 cycles.

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.  
tel: 413/772-2564 • fax: 413-772-2565 • web: [www.swmintl.com](http://www.swmintl.com) • email: [ams@swmintl.com](mailto:ams@swmintl.com)