

| General Description and Use | | |
|----------------------------------|--|----------------------|
| Argotec SKU Number | 29300 | |
| Typical application | General purpose adhesive film | |
| Polymer | Thermoplastic polyurethane, aromatic polyester | |
| Extrusion method | Cast film | |
| Gauge | 1.0 - 5 mils (25 - 125 microns) | |
| Width | Up to 60 inches (1.52 meters) | |
| Length | Up to 1000 non-spliced yards (914.4 meters) | |
| Key attributes | <ul style="list-style-type: none"> ■ Smooth and matte surfaces ■ Hard ester ■ Low softening temperature | |
| Typical Properties | Test Method | Value |
| Durometer | ASTM D-2240 | Shore 90A |
| Tensile stress @ 100% elongation | ASTM D-412 | 850 psi 5.9 MPa |
| Tensile stress @ 300% elongation | | 1140 psi 7.9 MPa |
| Tensile strength | | 5900 psi 40.7 MPa |
| Elongation at break | | 640% |
| Tear strength | D-624 ¹ | 430 pli 75.3 kN/m |

¹ Die C.

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.
tel: 413/772-2564 • fax: 413-772-2565 • web: www.swmintl.com • email: ams@swmintl.com