

General Description and Use		
Argotec SKU Number	18433	
Typical application	Textile lamination; flame Resistant	
Polymer	Thermoplastic polyurethane, aromatic polyether	
Extrusion method	Blown film	
Gauge	1.0 - 10 mils (25 - 250 microns)	
Width	Up to 86 inches (2.2 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> ■ Smooth surface ■ Soft ether ■ Mid-range softening temperature ■ UL-94 V2 ■ FAR 25.853 (A) 	
Typical Properties	Test Method	Value
Durometer	ASTM D-2240	Shore 86A
Tensile stress @ 100% elongation	ASTM D-412	850 psi 5.9 MPa
Tensile stress @ 300% elongation		1900 psi 13 MPa
Tensile strength		7500 psi 38 MPa
Elongation at break		595%
Tensile set at 200% E		71%
Tear strength	D-624 ¹	500 pli 88 kN/m
Abrasion resistance	D-1044 ²	35 mg loss

¹ Die C.

² Taber abrasion CS-17 wheel, 1000 gm weight, 1000 cycles.

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.
tel: 413/772-2564 • fax: 413-772-2565 • web: www.swmintl.com • email: ams@swmintl.com