

| General Description and Use | | |
|----------------------------------|--|---------------------|
| Argotec SKU Number | 18452-FR | |
| Typical application | Die cut and seal | |
| Polymer | Thermoplastic polyurethane, aromatic polyether | |
| Extrusion method | Flat die | |
| Gauge | 5 - 80 mils (125 - 2000 microns) | |
| Width | Up to 60 inches (1.52 meters) | |
| Length | Up to 1000 non-spliced yards (914.4 meters) | |
| Key attributes | <ul style="list-style-type: none"> ■ Matte 2 surface ■ Soft ether ■ Mid-range softening temperature ■ FAR 25.853A ■ FMVSS-302 | |
| Typical Properties | Test Method | Value |
| Durometer | ASTM D-2240 | Shore 86A |
| Tensile stress @ 100% elongation | ASTM D-412 | 1100 psi 7.6 MPa |
| Tensile stress @ 300% elongation | | 1750 psi 12 MPa |
| Tensile strength | | 4800 psi 33 MPa |
| Elongation at break | | 640% |
| Tensile set at break | | 70% |
| Tear strength | D-624 ¹ | 600 pli 105 kN/m |
| Abrasion resistance | D-1044 ² | 30 mg loss |

¹ Die C.

² Taber abrasion H-18 wheel, 1000 gm weight, 1000 cycles.

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.
tel: 413/772-2564 • fax: 413-772-2565 • web: www.swmintl.com • email: ams@swmintl.com