

General Description and Use		
Argotec SKU Number	TX-1540	
Typical application	Performance apparel & footwear, medical	
Polymer	Thermoplastic polyurethane, aromatic polyether	
Extrusion method	Cast-on-polyethylene carrier	
Gauge	≥ 0.6 - 5.0 mils (15 - 125 microns)	
Width	Up to 68 inches (1.73 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> ■ Waterproof-breathable ■ Very high MVTR ■ Gloss, smooth or matte surface ■ Soft, quiet, excellent stretch & recovery ■ No processing additives to effect adhesion 	
Typical Properties	Test Method	Value
Specific gravity	D-792	1.22
Durometer	ASTM D-2240	80A
Tensile strength	ASTM D-412	4000 - 5000 psi (27.6 - 34.5 MPa)
Elongation		600 - 700%
Modulus (100%)		550 - 650 psi 3.8 - 4.5 MPa
Tensile set @ 200% elongation		<40%
MVTR 0.5 mil (12 microns) 0.6 mil (15 microns) 1.0 mil (25 microns)	E-96, procedure B upright, 73°F (23°C) at 50% RH	— 800 - 900 g/m ² /24 hr 700 - 800 g/m ² /24 hr

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.
tel: 413/772-2564 • fax: 413-772-2565 • web: www.swmintl.com • email: ams@swmintl.com