

General Description and Use		
Argotec SKU Number	<b>TX-2060</b>	
Typical application	Performance apparel & footwear	
Polymer	Thermoplastic copolyester	
Extrusion method	Flat die	
Gauge	≥ 0.2 - 6 mils (5-152 microns)	
Width	Up to 68 inches (1.73 meters)	
Length	Up to 1000 non-spliced yards (914.4 meters)	
Key attributes	<ul style="list-style-type: none"> <li>■ Waterproof-breathable</li> <li>■ Gloss, smooth or matte surface</li> <li>■ Soft, quiet, excellent stretch &amp; recovery</li> <li>■ No processing additives</li> <li>■ Good chemical resistance</li> <li>■ Good hi-temperature resistance</li> <li>■ No swelling or distortion from water soaking</li> </ul>	
Typical Properties	Test Method	Value
Specific gravity	D-792	1.20
Durometer	ASTM D-2240	45D
Tensile strength	ASTM D-412	2000 - 3000 psi (13.8 - 20.68MPa)
Elongation		600 - 700%
Melting point	D-3418	392 F° 200 C°
Tear (die C)	D-1004	240 - 260 Graves g/0.001"
Moisture vapor transmission	E-96 procedure B upright, 73°F (23°C) at 50% RH	850 g/m <sup>2</sup> /24 hr
0.5 mil (12 microns)		—
0.6 mil (15 microns)		725 g/m <sup>2</sup> /24 hr
1.0 mil (25 microns)		

Product information revised: July 1, 2014

All statements, product characteristics, and performance data contained herein are believed to be reliable based on observation and testing, but no representations, guarantees, or warranties of any kind are made as to accuracy, suitability for particular applications, or the results to be obtained. Nothing contained herein is to be considered to be permission or a recommendation to use any proprietary process or technology without permission of the owner. No warranty of any kind, expressed or implied, is made or intended.

SWM INTL

53 Silvio O. Conte Drive • Greenfield, Massachusetts 01301 U.S.A.  
tel: 413/772-2564 • fax: 413-772-2565 • web: [www.swmintl.com](http://www.swmintl.com) • email: [ams@swmintl.com](mailto:ams@swmintl.com)